

Connoisseur 100% Cotton



Common Attributes	Units	Test Method	110gsm	160gsm	300gsm
Wood Pulp & Bleach Type			ECF Cotton Linters, FSC ECF Virgin Woodfree		
Printing Process Suitability			Litho, Letterpress, Silk Screen, Dry Offset (Toray)		
Mono laser Guaranteed			✓	Not guaranteed for office print technologies	
Colour Laser Guaranteed			✓		
Mono Ink Jet Guaranteed			✓		
Colour Ink Jet Guaranteed			✓		
Recommended p.H. of Fount Solution			5.5 ± 0.5		
Surface p.H.		TAPPI 5290M	<<----- ≈ 6.5 ----->>		7,5
None Aging Credentials		ISO 9706	no but>100 yrs	no but>100 yrs	Yes
Environmental Label		ISO 14001	Yes		
Quality Management		ISO 9002 : 2000	Yes		
Moisture Content	%	ISO 287	6		6,5
Relative Humidity	%	TAPPI T502	40 - 60		
Caliper	µm	ISO 534	165	256	475
Whitest Shade Opacity	%	ISO 2471	92	96	N/A
Bendtsen Roughness	ml/min	ISO 2494	1000	1000	1000
Stiffness M Direction	mN	ISO 2493	240	400	160
C Direction		L+W, <i>TABER</i>	120	200	80

These specifications are the property of Arjo Wiggins Fine Papers Ltd and may be changed without prior notice. They are target values only for use as a guide.